

Specification: ARA-LT[®] „Black“

Laser-transferable PVD-coatings with Silicium-Titanium and their oxides on PET-films Article no.: 2.00.804.00

Description

ARA-LT[®] „Black“ consists of Silicium-Titanium and there oxide on a PET film. The PET film is transparent for the laser wave length used (1064 nm) and acts as a carrier for the black coating to be transferred.

Depending on the purpose of use and on the product surface, the black coating may be embedded between a release layer and a thin adhesive layer.

The whole coating is made by using the vacuum based coating technology Physical Vapor Deposition (“PVD”).

The coated PET-film is rolled up on a roll core in such a way, that the PVD-coating is located on the inner side.

Purpose of use

With ARA-LT[®] „Black“ different products can be equipped to get decorative and extremely robust markings with excellent mechanical and chemical properties.

To do so, a standard marking laser is necessary only.

A description about how it works is given in the operation manual.

When the selective transfer of the black coating was proceeded correctly, for example on ceramic or glass surfaces, then the remaining black marking is opaque, very abrasion resistant and shows an excellent adhesion.



Photo: Laser-induced PVD-marking on ceramic and glass, showing a “ship”

Examples for suitable product materials to be equipped with ARA-LT[®] „Black“ are glass, steel, ceramics and some polymers.

Technical data

PET film

The corresponding data sheet is given upon request. The standard thickness of

the PET carrier is 72 µm and its width is 30 mm. Depending on request, ARA-LT® “Black” coated PET-films with thicknesses between 12 µm and 100 µm and a width between 10 mm and around 600 mm can be delivered.

PVD-coating

The transferable black coating consists of Silicium-Titanium and there oxide with a thickness between 300 nm and 400 nm.

Properties of the ARA-LT® “Black” - coated PET-film

- It's mechanical, chemical und thermal resistance is limited by the PET carrier itself (please see the corresponding data sheet).
- Storage conditions: 8-25 °C; RH <60 %; one year

Properties of the transferred black layer

The mechanical, chemical and thermal properties as written below are valid only in case of a correct transfer on a suitable product surface.

- Optical appearance: black
- Strong contrast, sharp edges – even on very small graphics and structures
- Adhesion and abrasion resistance: excellent
- Chemical stability: not affected by standard cleaning agents, acids and bases; sterilizable
- Thermal stability: up to 400 °C
- Corrosion resistant
- The product surface is not affected by the PVD-marking process
- The manufacturing is environmentally friendly

Contact

Ara-Coatings GmbH & Co. KG
Gundstr. 13
91056 Erlangen
Deutschland

Telefon: +49 (0) 9131 907040
Fax: +49 (0) 9131 9070444
Mail: info@ara-coatings.de
Website: www.ara-coatings.de